

# Hempel's Wood Impreg 02362

## Product characteristics

### Description

Hempel's Wood Impreg is a clear alkyd oil with good penetration properties. Used to saturate wood before application of varnish or paint systems.

### Recommended use

For use as a first coat for wooden boats and hardwood, interior and exterior, above the waterline.

### Features

- Not available.

## Product safety

**Flash point** 102°F [39°C]

### VOC content

Legislation	Value
EU	4.82 lb/US gal [578 g/L]

According to specific legislation, see details in the Explanatory Notes available at Hempel website, [hempel.com](http://hempel.com) or at your local Hempel website.

### Handling

Handle with care. Before and during use, observe safety labels on packaging and paint containers and follow all local and national safety regulations. Always consult Hempel's Safety Data Sheet for this product along with the Product Data Sheet.

## Product data

### Product code

02362

### Standard shade / code

Transparent 00000

### Volume solids

25 ± 2%

### Specific gravity

7 lb/US gal [0.8 kg/L]

### Reference dry film thickness

0.8 mils [20 micron]

## Surface preparation

### Cleanliness

- Remove oil, grease and other contaminants by suitable detergent cleaning.

### New build:

- The surface must be dry and clean prior to application.  
- Moisture content of the wood must be below 16%.

### Maintenance and Repair

- Previously treated wood: Remove dust and loose material.

## Application

### Thinner

Hempel's Thinner 811 08111

### Cleaner

Hempel's Thinner 811 08111

# Hempel's Wood Impreg 02362

## Application method

Tool	Thinning max vol.
Brush	20%

Keep thinning at an absolute minimum.

## Film thickness

	Recommended
Theoretical spreading rate	530 sq ft/US gal [13 m <sup>2</sup> /L]

Spreading rate will depend on surface roughness, porosity of the substrate and application method.

## Application conditions

- To avoid condensation, apply on a clean and dry surface with a temperature that is at least 5°F [3°C] above the dew point.

## Relative Humidity:

- Relative humidity must be below 85% during drying and curing.

## Application remarks

- Stir well before use.
- Depending on porosity of the wood, apply 2-4 coats of the product wet on wet.
- Allow the oil to absorb into the wood.
- Remove surplus with a clean lint-free cloth to avoid film-forming.
- Allow to dry.
- Overcoat with required Hempel varnish or paint system.

## Drying and overcoating

### Product compatibility

- Previous coat: None.
- Subsequent coat: Recommended products are: Hempel's varnishes or paint systems.

## Drying time

Surface temperature		50°F [10°C]	68°F [20°C]
Touch dry	hours	12	6

Determined for dry film thickness NaN mils [NaN micron] at standard conditions, see Hempel's Explanatory Notes for details.

## Drying conditions

- Condensation on the freshly applied coating should be avoided.

## Other remarks

- The surface must be clean before overcoating.

## Storage

### Shelf life

Ambient temperature	77°F [25°C]
Product	60 months

Shelf life from date of production, when stored in original, unopened containers. Thereafter, the product quality must be re-inspected. Always check the best before date or expiry date on the label.

## Storage conditions

- Product must be stored according to local legislation, at 5°C [41°F] without direct sunlight and protected from rain and snow.

## Carbon Footprint

Dry film thickness	1 mil	1 µm
GWP (Global Warming Potential)	0.073 lb CO <sub>2</sub> e/ft <sup>2</sup>	14 g CO <sub>2</sub> e/m <sup>2</sup>

The carbon footprint is for 1 square meter / square foot of surface area with a dry film thickness of 1 micron / mil.

The scope includes raw materials, in-bound transport to the Hempel factory, Hempel manufacturing processes, and any Volatile Organic Compounds emitted during and after the application of the product.

# Hempel's Wood Impreg 02362

It is calculated based on the standard shade defined in this PDS.  
Values may vary with shade.

## Additional documents

Additional information is available at the Hempel website  
<https://www.hempel.com/service-and-support/technical-guidelines>  
or at your local Hempel website:

- Explanatory Notes explaining the fields in this Product Data Sheet.
- Surface Preparation Guidelines.
- Application Guidelines for different application methods.
- Further information: Hempel Yacht Paint Manual and [hempelyacht.com](http://hempelyacht.com)

This Product Data Sheet ("PDS") relates to the supplied product ("Product") and is subject to updating from time-to-time. Accordingly, the buyer/applicator should have regard to the PDS supplied together with the relevant batch of the Product (and not an earlier version). In addition to the PDS, the buyer/applicator may receive some or all of the following specifications, statements and/or guidelines as listed below or as are available from the Hempel website under 'Products' at [www.hempel.com](http://www.hempel.com) (the "Additional documents"):

No.	Document description	Location/comments
1.	Technical Statement	One-off specific advice provided on request for specific projects
2.	Specification	Only issued for specific projects
3.	PDS	This document
4.	Explanatory Notes to the PDS	Available at <a href="http://www.hempel.com">www.hempel.com</a> and contain relevant information about the Product testing parameters
5.	Application Instruction	Where available, at <a href="http://www.hempel.com">www.hempel.com</a>
6.	Generic technical guidelines (e.g. on application and surface preparation)	Where available, at <a href="http://www.hempel.com">www.hempel.com</a>

In the event of a conflict of information between the PDS and the Additional documents, the order of priority of information shall be in the order as set out above. In such event you should also contact your representative at Hempel for clarification. Furthermore, the buyer/applicator must have full regard to the relevant Safety Data Sheet provided with each Product and which can also be downloaded from [www.hempel.com](http://www.hempel.com).

Hempel shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements set out in the relevant PDS and the Additional Documents. The information and terms of this disclaimer apply to this PDS, the Additional documents and any other documents supplied by Hempel in respect of the Product. In addition, the Product is supplied and all technical assistance is given subject to Hempel's General Conditions of Sale, Delivery and Service, unless otherwise expressly agreed in writing.